



Extraction of Cellulose Nanocrystals (NCC) from Cotton Waste and Morphology of NCC Obtained with Different Alkali Neutralization

Fabrizio Scognamiglio¹, Carlo Santulli^{2*} and Graziella Roselli¹

¹*School of Sciences and Technologies, Università di Camerino, Chemistry Division, via Sant'Agostino 1, 62032 Camerino, Italy.*

²*School of Architecture and Design, Università di Camerino, Viale della Rimembranza 9, 63100 Ascoli Piceno, Italy.*

Authors' contributions

This work was carried out in collaboration among all authors. Author FS managed the literature search and performed the statistical analysis. Author GR designed the study and suggested the protocol. Author CS commented on experiment results, contributed to literature search and wrote the first draft of the paper. All authors read and approved the final manuscript.

Article Information

DOI: 10.9734/CJAST/2019/v36i530254

Editor(s):

(1) Dr. Aleksey Aleksandrovich Hlopitskiy, Professor, Department of Technology Inorganic Substances, Ukrainian State University of Chemical Technology, Ukraine.

Reviewers:

(1) C. Umeileka Chisom, University of Portharcourt, Nigeria.

(2) Yongchun Zhu, Shenyang Normal University, China.

(3) Emmanuel M. Papamichael, University of Ioannina, Greece.

Complete Peer review History: <http://www.sdiarticle3.com/review-history/50077>

Original Research Article

Received 07 May 2019

Accepted 13 July 2019

Published 29 July 2019

ABSTRACT

The extraction of cellulose nanocrystals (NCC) from cotton textile waste, constituted by 70% long fibers and 30% cotton linter, was performed through the action of sulfuric acid followed by solution neutralization with two different alkalis, namely ammonia and sodium bicarbonate, which yielded microcellulose (MCC), then centrifuged to NCC. The action of the two alkalis was compared as for fiber repeatability and morphology, and the results obtained using ammonia were considered more suitable for possible introduction of NCC for the repair of historical paper artifacts. This evidence was obtained by applying optical/polarized light microscopy observation and dynamic light scattering (DLS) results.

*Corresponding author: E-mail: carlo.santulli@unicam.it;

Keywords: Cotton waste; nanocellulose extraction; alkali neutralization; Dynamic Light Scattering (DLS).

1. INTRODUCTION

Extraction of cellulose nanocrystals (NCC) from cellulosic solid residue (CSR) represents an important way of upcycling it, therefore obtaining a material with some value, hopefully with a reasonable yield that would make the extraction worthwhile. Overtime the extraction of NCC has been performed from wastes obtained from the productive systems of different natural fibers, with the idea of operating as much as possible in conditions of circular economy, therefore using a zero waste strategy [1]. A common procedure for the purpose used involves the use of an acid solution, so to obtain hydrolysates of the waste stream: this is most frequently performed with sulfuric acid, and then neutralized using an alkaline solution [2]. Cellulosic waste stream from which NCC have been extracted includes, among others, materials from a large number of plants, in particular oil palm [3], pineapple leaves [4], Phormium tenax [5], hemp [6], okra bahmia [7], etc. In most cases the application of NCC, once extracted, has been their use as the reinforcement of polymer matrices, such as poly(vinylalcohol) (PVA) [8], etc. More recent studies have broadened even more the range of fibers, which can provide waste material for NCC extraction, with very variable yield, due to the different characteristics of plants, such as it is shown for example in [9-11].

In terms of practical use though, one of the main cellulosic products is represented by cotton, which is an abundant waste from textiles production and is basically almost pure cellulose, reaching up to 90% in weight. Cotton normally used in the textile industry is in the range that is indicated as medium length fibers, hence between 18 and 28 mm long. In contrast, shorter (cotton linter) and longer fibers are mostly considered as waste, therefore it can be deemed suitable for the extraction of nanocellulose. In general terms, it proved effective for the purpose, whether colored or not, despite some differences in yield, in sulfonation efficiency and thermal stability [12]. More specifically, a study on the extraction of NCC from cotton linter originating from Brazil did demonstrate that controlling waste stream for extraction may result in a more uniform quality product: cotton linter is particularly adapted, in that it does not require pulping before extraction [13].


The particular aim of this study is to extract and characterize the morphology of cotton waste used, which results from discarded materials obtained from the development of pure cellulose paper products at a dedicated technical school in Fabriano, Italy. The idea is to possibly use the nanocellulose resulting as a material for restoration of precious ancient paper artifacts. However, the present work concentrates on the feasibility of the method and on the morphology of nanocellulose obtained using two different alkalis, namely sodium bicarbonate and ammonia.

2. MATERIALS AND METHODS


2.1 Extraction

Crystalline nanocellulose (NCC) has been extracted starting from a raw mixed waste material consisting approximately of 100 mL of 70% long bleached fiber from cotton mass and 30% short fiber from cotton linter with bulk density of 0.6 g/mL; this yielded 2.9 g of cellulose through hydrolysis with 110 ml of H₂SO₄ 96 wt%, T = 45°C ÷ 50°C, mechanical stirring, t = 3h 45 min) followed by the addition of 600 ml of icy distilled water to stop the hydrolysis. After this, decantation for one night was performed, followed by cycles of centrifugation (7000 rpm, t = 30 min) and washing with distilled water until a neutral pH is achieved. The final stage was composed by dialysis and sonication. The total NCC solution (approximately 150 ml) obtained was characterized by dynamic light scattering (DLS).

Two different alkalis, namely sodium bicarbonate and ammonia, were attempted to neutralize the solution, with attention to have the most repeatable and less dispersed fiber morphology. The neutralization was carried out with sodium bicarbonate according to the reaction:



and using ammonia according to the reaction:



2.2 Dynamic Light Scattering (DLS)

Different microscopy images have been acquired, at magnifications between x10 and

x20, from a MT9200 Meiji Techno Co., Japan, polarized light optical microscope, equipped with a DeltaPix camera, subsequently Dynamic Light Scattering using a Malvern Zetasizer analyzer to obtain a size distribution of the fiber obtained.

Dynamic Light Scattering (DLS) is a non-invasive technique for the measurement of the dimension of molecules, nanoparticles or colloids, at dimensions under the micron and in this specific case it has been used to measuring the hydrodynamic diameter following from diffusion measurements, according to the Stokes-Einstein equation [14]. To obtain different evaluations of the cellulose fibers sizes, for a sounder reliability of the test, three DLS measurements were carried out on a 1 ml solution. The second and the third measurements were performed after 5 and 10 minutes from the first one, respectively.

Since the extraction yielded microcrystalline fibers, these underwent further to a centrifugation cycle at 7000 rpm, for 30 minutes, as reported above, in order to separate the dimensionally larger fraction from the supernatant, which constituted the nanometric fraction.

3. RESULTS AND DISCUSSION

After the process of sulfonation and subsequent neutralization, microcellulose was obtained, whose characteristics are reported in Figs. 1-2 (ammonia neutralization) and Figs. 3-4 (sodium

bicarbonate neutralization). In Figs. 1 and 3 fiber distribution in a drop of solution is shown under polarized light. In the case of ammonia neutralized microcellulose fibers, a considerable part of the material extracted has similar optical properties, yielding a more uniform color over fiber surface. This indicates both that their surface is even, and that they are also mechanically more regular. Also the limited presence of detached parts from the fiber suggests the possibility of a more frequent cylindrical geometry for fibers in Fig. 1 than in Fig. 3. Aspect ratios i.e., length/diameter of the fibers, appear to be the most various, although in general they are for both neutralization methods mostly above 10, therefore providing some prospective reinforcement effect for the introduction in a polymer matrix, such as e.g., poly(vinylalcohol) (PVA) [15].

In Figs. 2 and 4 some isolated fibers are depicted under normal light. In this case, striations were in particular observed in the micrographs, which are an indication that orientation of the filaments occurred, producing material with fibrillar morphology. This would lead as a result to a higher effect of tensile reinforcement for the microfiber, provided filaments not tend to be at an angle or detach from the bulk of the fiber, a case which is termed as “fibrillation” and leads to more mechanical inconsistency [16]. Fibrillation appears more frequent with the sodium bicarbonate neutralized fibers in Fig. 4.




Fig. 1. Optical polarized light micrograph of cellulose extracted using NH₃ neutralization, before centrifugation



Fig. 2. Optical micrograph of cellulose extracted using NH_3 neutralization, before centrifugation




Fig. 3. Optical polarized light micrograph of cellulose extracted using NaHCO_3 neutralization, before centrifugation




Fig. 4. Optical micrograph of cellulose extracted using NaHCO_3 neutralization, before centrifugation

The distribution of the fibers, as from DLS graph, did appear to present a number of peaks and also the three measurements on the same solution did not appear to be superposed, which suggests a scarce reliability of the measure, for neutralization with both alkalis (Fig. 5 for ammonia and 6 for sodium bicarbonate). This is considerably worsened in the case of neutralization with sodium bicarbonate, where the peaks revealed do not appear having any real correspondence in the three tests carried out.

after centrifugation are of nanometric dimension and therefore not apparent in the optical microscope image at 20x magnification.

After centrifugation, the evaluation carried out using DLS confirm the superiority of ammonia neutralization also in the case of NCC, since the dimensions appear more repeatable and less scattered with a statistical mode consistently in the region of 500 nm (Fig. 8). In contrast, in the case of sodium bicarbonate neutralization, it has been observed that the above statistical mode is only clearly indicated in one of the three measurements, in the other cases the values are still quite dispersed and confused (Fig. 9).

As it is possible to notice in Fig. 7, referred to ammonia-extracted fibers, the fibers obtained




Fig. 5. DLS distribution of cellulose extracted using NH₃ neutralization, before centrifugation




Fig. 6. DLS distribution of cellulose extracted using NaHCO₃ neutralization, before centrifugation




Fig. 7. Micrograph of cellulose extracted using NH_3 neutralization




Fig. 8. DLS distribution of cellulose extracted using NH_3 neutralization, after centrifugation




Fig. 9. DLS distribution of cellulose extracted using NaHCO_3 neutralization, after centrifugation

4. CONCLUSION

The extraction of cellulose nanocrystals (NCC) from cotton textile waste (70% long fibers and 30% cotton linter) through the action of sulfuric acid followed by solution neutralization with two different alkalis, namely ammonia and sodium bicarbonate proved effective in general terms. This yielded microcellulose (MCC) of good quality and uniformity, although in the latter case the fibers were thinner and of less regular shape than in the former one. A subsequent action of centrifugation led to obtaining NCC. Comparing the action of the two neutralizing alkalis, the materials obtained using ammonia can be considered superior. The evidence provided by optical/polarized light microscopy observation and dynamic light scattering (DLS) results suggested a higher geometrical regularity and fibrillar adhesion, together with a lower dimensional dispersion with respect to those yielded by applying sodium bicarbonate neutralization. The result of this study, hence the superiority of ammonia for the neutralization process, is considered of interest to prepare the procedure of extraction for the introduction of NCC for the repair of historical paper artifacts.

COMPETING INTERESTS

Authors have declared that no competing interests exist.

ACKNOWLEDGEMENTS

For useful advice and availability of the testing labs. the authors wish to acknowledge the contribution of Dr. Serena Gabrielli, Dr. Cristina Cimarelli and Prof. Enrico Marcantoni, of the School of Sciences and Technologies, Università di Camerino, and for DLS distribution tests of Dr. Stefania Pucciarelli, of the School of Biosciences and Veterinary Medicine, Università di Camerino.

REFERENCES

1. Wang Q, Zhu JY, Considine JM. Strong and optically transparent films prepared using cellulosic solid residue recovered from cellulose nanocrystals production waste stream, *ACS Appl Mater Interfaces*. 2013;5(7):2527-2534.
2. Bondeson D, Mathew A, Oksman K. Optimization of the isolation of nanocrystals from microcrystalline cellulose by acid hydrolysis, *Cellulose* 2006;13:171.
3. Lani NS, Ngadi N, Johari A, Jusoh M. Isolation, characterization and application of nanocellulose from oil palm empty fruit bunch fiber as nanocomposites. *J Nanomater*. 2014;13.
4. Cherian BM, Leão AL, Ferreira de Souza S, Thomas S, Pothan LA, Kottaisamy M. Isolation of nanocellulose from pineapple leaf fibres by steam explosion, *Carbohydr Polym*. 2010;81(3):720-725.
5. Fortunati E, Puglia D, Monti M, Santulli C, Kenny JM. Extraction of cellulose nanocrystals from *Phormium tenax* fibres, *J Polym Environ*. 2013;21(2):319-328.
6. Luzi F, Fortunati E, Puglia D, Lavoragna M, Santulli C, Kenny JM, Torre L. Optimized extraction of cellulose nanocrystals from pristine and carded hemp fibres, *Ind Crops Prod*. 2014;56:175–186.
7. Fortunati E, Puglia D, Monti M, Santulli C, Maniruzzaman M, Kenny JM. Cellulose nanocrystals extracted from okra fibres in PVA nanocomposites. *J Appl Polym Sci* 2013;128(5):3220–3230.
8. Coelho de Carvalho Benini KC, Cornelis Voorwald HJ, Hilário Cioffi MO, Milanese AC, Ornaghi Jr. HL. Characterization of a new lignocellulosic fiber from Brazil: *Imperata brasiliensis* (Brazilian Satintail) as an Alternative Source for Nanocellulose Extraction, *J Natural Fib*. 2017;14(1):112-125.
9. Mariño M, Lopes da Silva L, Durán N, Tasic L. Enhanced Materials from Nature: Nanocellulose from citrus waste. *Molecules*. 2015;20(4):5908-5923.
10. Szlapak Franco T, Potulski DC, Viana LC, Forville E, de Andrade AS, Bolzónde Muniza GI. Nanocellulose obtained from residues of peach palm extraction (*Bactris gasipaes*), *Carbohydr Polym*. 2019;218:8-19.
11. Fortunati E, Luzi F, Puglia D, Terenzi A, Vercellino M, Visai L, Santulli C, Torre L, Kenny JM. Ternary PVA nanocomposites containing cellulose nanocrystals from different sources and silver particles: Part II, *Carbohydr Polym*. 2013;97(2):837–848.
12. de Moraes Teixeira E, Corrêa AC, Manzoli A, de Lima Leite F, Ribeiro de Oliveira C, Capparelli Mattoso LH. Cellulose nanofibers from white and naturally colored cotton fibers, *Cellulose*. 2010;17(3):595–606.

13. Saraiva Morais JP, Morsyleide de Freitas R, Moreira de Souza Filho M, Dias Nascimento L, Magalhães do Nascimento D, Ribeiro Cassales A. Extraction and characterization of nanocellulose structures from raw cotton linter, Carbohydr Polym. 2013;91(1):229-35.
14. Pecora R. Dynamic light scattering measurement of nanometer particles in liquids. Journal of Nanoparticle Research. 2000;2(2):123–131.
15. Lee SY, Jagan Mohan D, Kang IA, Doh GH, Lee S, Ok Han S. Nanocellulose reinforced PVA composite films: Effects of acid treatment and filler loading. Fibr and Polym. 2009;10(1):77–82.
16. Haapala A, Laitinen O, Karinkanta P, Liimatainen H, Niinimäki J. Optical characterisation of size, shape and fibrillarity from microfibrillar and microcrystalline cellulose and fine ground wood powder fractions, Appita Technology, Innovation, Manufacturing, Environment. 2013;66(4): 331-339.

© 2019 Scognamiglio et al.; This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Peer-review history:

*The peer review history for this paper can be accessed here:
<http://www.sdiarticle3.com/review-history/50077>*